

Intertek

ETL SEMKO

TEST REPORT

ASTM E84-05

SURFACE BURNING CHARACTERISTICS OF BUILDING MATERIALS

Report No. 3090554SAT-001-Rev. 01

P1300 Wall and Ceiling Panel

March 8, 2005

Prepared for:

Extrutech Plastics, Inc.
5902 West Custer Street
Manitowoc, WI 54220

**Intertek Testing
Services NA, Inc.**

16015 Shady Falls Road
Elmendorf, TX 78112
(voice) 210-635-8100
(fax) 210-635-8101
[www.intertek-
etlsemko.com](http://www.intertek-etlsemko.com)

ABSTRACT

Test Specimen: **P1300 Wall and Ceiling Panel**

Test Standard: **ASTM E84-05**


Test Date: **March 02, 2005**

Test Sponsor: **Extrutech Plastics, Inc.**

Test Results:

| | | |
|-----------------------|---|-----|
| FLAME SPREAD INDEX | = | 40 |
| SMOKE DEVELOPED INDEX | = | 300 |
| | = | |

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to copy or distribute this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.



Eric G. Hutchinson
Project Manager

March 8, 2005

Reviewed and approved:



C. Anthony Peñaloza
Flammability Testing Team Leader

March 8, 2005