

Intertek

TEST REPORT

ASTM E84-08

**SURFACE BURNING
CHARACTERISTICS
OF BUILDING MATERIALS**

Report No. 3177356SAT-001A

P1300 - 12" Panel

April 17, 2009

Prepared for:

Extrutech Plastics, Inc.
5902 West Custer Street
Manitowoc, WI 54220

Intertek Testing
Services NA, Inc.
16015 Shady Falls Road
Elmendorf, TX 78112
(voice) 210-635-8100
(fax) 210-635-8101
[www.intertek-
etlsemko.com](http://www.intertek-etlsemko.com)

Extrutech Plastics, Inc.

ABSTRACT

Test Specimen: P1300 - 12" Panel

Test Standard: ASTM E84-08


Test Date: April 15, 2009

Test Sponsor: Extrutech Plastics, Inc.


Test Results:

FLAME SPREAD INDEX	=	20
SMOKE DEVELOPED INDEX	=	400
	=	N/A ft. Beyond Burners Centerline

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to copy or distribute this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.


Teodoro Alvarado Jr
E84 OperatorApril 17, 2009

Reviewed and approved:


Miguel Zamarripa
Project ManagerApril 17, 2009**Intertek**